



H.S. WHITE CORPORATION

Marine and Industrial Specialties

1350 S. Dixie Highway East • Pompano Beach, FL 33060
 Pompano (954) 785-6760 Miami (305) 940-2700 W.P.B. (561) 832-4144
 Fax (954) 785-8247 Website: www.HSWHITE.com

Teflon® Virgin PTFE (Polytetrafluoroethylene) Sheet and Film STYLE 8765

Manufactured from PTFE, this sheet is ideal for a wide range of gasketing applications. Food and chemical applications are often sealed using PTFE. PTFE resin sheets are available in both Virgin, Mechanical and Expanded (EPTFE) grades.

PTFE is resistant to acids, alkalais, solvents or corrosives. Extremely low coefficient of friction, thus eliminating any stick/slip effect. Extremely anti-adhesive.

TENSILE: 2800

ELONGATION: 270

Property	Units	Typical Values ¹
Specific Gravity	g/cc	2.14-2.20
Hardness	Shore D	52-65
Deformation Under Load (73°F., 2000 psi, 24hrs.)	%	15-16
Coefficient of Linear Thermal Expansion (78°F.-400°F.)	In./in./ °F	4-9 x 10 ⁻⁵
Thermal Conductivity	BTU/hr./ft. ² /F.in	1.7
Volume Resistivity	ohm-cm	>10 ¹⁵
Dielectric Strength	volts/mil	300 min

¹The measured values expressed in ranges reflect measurements made both with and across the molding direction of the product.

WARNING: Properties shown on this document are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations, consult H.S.White. While the utmost care has been used in compiling this document,



H.S. WHITE CORPORATION

Marine and Industrial Specialties

1350 S. Dixie Highway East • Pompano Beach, FL 33060
Pompano (954) 785-6760 Miami (305) 940-2700 W.P.B. (561) 832-4144
Fax (954) 785-8247 Website: www.HSWHITE.com

we assume no responsibility for errors. This edition cancels all previous issues. Subject to change without notice.